

STEREOLITHOGRAPHY ABS-LIKE WHITE

Current Supplier Material:
[Accura Xtreme White 200](#)



PRODUCT DESCRIPTION

ABS-Like White is a widely used, all-purpose material that provides flexibility relative to other SLA resins. It is an ideal stereolithography material for durability. Compared to the average value for injection-molded ABS, it will have a slightly higher tensile strength but lower elongation at break. ABS-Like White's heat deflection is the lowest of all SLA materials.

APPLICATIONS

ABS-Like White's well-rounded mechanical properties make it suitable for form-and-fit prototypes, snap-fit assemblies, consumer electronic components, and medical device prototypes.



KEY PRODUCT BENEFITS

- Good strength and flexibility
- Durability
- Dimensional Stability

PROPERTIES

PROPERTY	TEST METHOD	VALUE
Color	-	White
Density in solid state*	@ 25 °C (77 °F)	1.18 g/cm ³
Water absorption (20 °C, 50% relative humidity)	ASTM D570	0.65 ± 0.15%
E-module (x-y plane)	ASTM D638, test speed 10mm/min.	3,300 ± 400 MPa
Tensile strength (x-y plane)		55 ± 10 MPa
Elongation at break (x-y plane)		9 ± 5%
Heat deflection temperature @ 0.46 MPa*	ASTM D648	47 °C (117 °F)
Heat deflection temperature @ 1.82 MPa*		42 °C (108 °F)

[*From supplier data sheet](#)

TOLERANCES

For well-designed parts, tolerances in the X/Y dimension of ±0.002 in. (0.05mm) for the first inch plus ±0.001 in./in., and Z-dimension tolerances of ±0.005 in. (0.127mm) for the first inch plus ±0.001 in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.

CHINA METAL PARTS,
CORP.

China Metal Parts, Corp.
7th Industrial Zone, Shangnan, Shajing, Baoan, Shenzhen, China.
Zip Code: 518125 Tel: +86-755-27311095 Fax: +86+755-29918958
inquiry.us@made-parts.com us.mfgmachined.com