

STEREOLITHOGRAPHY ABS-LIKE TRANSLUCENT/CLEAR

Current Supplier Material: [WaterShed XC 11122](#)



PRODUCT DESCRIPTION

ABS-Like Translucent/Clear offers a unique combination of low moisture absorption and near-colorless transparency. Custom finishing is required to achieve functional clarity. Its tensile strength and elongation at break are among the highest of 3D-printed, thermoset materials.

APPLICATIONS

ABS-Like Translucent/Clear can be used for general-purpose applications but is ideal for flow-visualization models, microfluidics, and light pipes.



KEY PRODUCT BENEFITS

- Functional clarity
- Water resistant

PROPERTIES

PROPERTY	TEST METHOD	VALUE
Color	-	Translucent with Standard Finish / Clear with Custom Finish
Density in solid state*	@ 25 °C (77 °F)	1.12 g/cm ³
Water absorption (20 °C, 50% relative humidity)	ASTM D570	0.35 ± 0.15%
E-module (x-y plane)	ASTM D638, test speed 10mm/min.	2,900 ± 400 MPa
Tensile strength (x-y plane)		55 ± 10 MPa
Elongation at break (x-y plane)		6 ± 3%
Heat deflection temperature @ 0,46 MPa*	ASTM D648	45.9 - 54.5 °C (115 - 130 °F)
Heat deflection temperature @ 1,82 MPa*		49.0 - 49.7°C (120 °F)

[*From supplier data sheet](#)

TOLERANCES

For well-designed parts, tolerances in the X/Y dimension of ±0.002 in. (0.05mm) for the first inch plus ±0.001 in./in., and Z-dimension tolerances of ±0.005 in. (0.127mm) for the first inch plus ±0.001 in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.

**CHINA METAL PARTS,
CORP.**

China Metal Parts, Corp.
7th Industrial Zone, Shangnan, Shajing, Baoan, Shenzhen, China.
Zip Code: 518125 Tel: +86-755-27311095 Fax: +86+755-29918958
inquiry.us@made-parts.com us.mfgmachined.com