

# Stainless Steel AL 17-4™ Precipitation Hardening Alloy

(UNS Designation S17400)

## GENERAL PROPERTIES

Allegheny Ludlum's AL 17-4™ Precipitation Hardening Alloy (S17400), Type 630, is a chromium-nickel-copper precipitation hardening stainless steel used for applications requiring high strength and a moderate level of corrosion resistance. High strength is maintained to approximately 600°F (316°C).

The S17400 alloy is martensitic in structure in the annealed condition and is further strengthened by a low temperature treatment which precipitates a copper containing phase in the alloy. In comparison to many alloys in the precipitation hardening family, the S17400 alloy requires a simple heat treatment; a one step process conducted at a temperature in the range 900°F (482°C) to 1150°F (621°C) depending on the combination of strength and toughness desired. A wide range of properties can be produced by this one step heat treatment. Heat treatment in the 900°F (482°C) range produces highest strength, although slightly less than that of alloys like S17700 or S15700. The latter precipitation hardening alloys generally require more steps to complete heat treatment.

## FORMS AND CONDITIONS

The Allegheny Ludlum AL 17-4 Precipitation Hardening Alloy is furnished as plate. Long products are produced by Allvac, an Allegheny Technologies Company. In all forms, the material is furnished in the annealed condition.

| Element              | Typical Composition (Weight Percent) |
|----------------------|--------------------------------------|
| Carbon               | 0.04                                 |
| Manganese            | 0.40                                 |
| Phosphorus           | 0.020                                |
| Sulfur               | 0.005                                |
| Silicon              | 0.50                                 |
| Chromium             | 15.5                                 |
| Nickel               | 4.5                                  |
| Columbium + Tantalum | 0.30                                 |
| Copper               | 3.50                                 |
| Iron                 | Balance                              |

## SPECIFICATIONS

The AL 17-4 Precipitation Hardening Alloy (S17400) is covered by the following wrought product specifications.

| Specification             | Product Form                     |
|---------------------------|----------------------------------|
| AMS 5604                  | Sheet, Strip and Plate           |
| AMS 5643                  | Bars, Forgings, Tubing and Rings |
| AMS 5825                  | Welding Wire                     |
| AMS 5827                  | Welding Electrodes               |
| AMS 7474                  | Bolts                            |
| ASTM A 564<br>ASTM SA 564 | Bars, Wire and Shapes            |
| ASTM A 693<br>ASME SA 693 | Sheet, Plate and Strip           |
| ASTM A 705<br>ASME SA 705 | Forgings                         |

## CORROSION AND OXIDATION RESISTANCE

Tests have shown that the corrosion resistance of AL 17-4 Precipitation Hardening Alloy is comparable to that of Type 304 stainless steel in most media. In general, the corrosion resistance of AL 17-4 alloy is superior to that of the hardenable 400 series stainless steels.

As with other precipitation hardening alloys, AL 17-4 Precipitation Hardening Alloy is more susceptible to stress corrosion cracking at peak strength. Consequently, in applications in which chloride stress corrosion cracking is a possibility, the material should be precipitation hardened to produce the lowest hardness compatible with the intended end use. This is done by heat treating at the highest temperature which will produce suitable minimum properties.

Material in the annealed condition should not generally be put into service. In this condition, the material has an untempered martensite structure and is less ductile than aged material. The untempered martensite may be subject to unpredictable brittle fractures. In corrosive environments, the untempered martensite is more sensitive to embrittling phenomena such as hydrogen embrittlement than material which has had one of the precipitation hardening heat treatments. Similarly, untempered martensite is more sensitive to chloride stress corrosion cracking than material in which the martensite has been tempered.

The oxidation resistance of the AL 17-4 alloy is superior to that of 12 percent chromium alloys like Type 410, but slightly inferior to that of Type 430. Precipitation hardening will produce surface oxidation.

## PHYSICAL PROPERTIES

|                                                                                                                | Condition<br>A                                  | Condition<br>H 900 | Condition<br>H 1075 | Condition<br>H 1150 |
|----------------------------------------------------------------------------------------------------------------|-------------------------------------------------|--------------------|---------------------|---------------------|
| <b>Density</b><br>lb / in <sup>3</sup><br>g / cm <sup>3</sup>                                                  | 0.280<br>7.75                                   | 0.282<br>7.81      | 0.283<br>7.83       | 0.284<br>7.86       |
| <b>Linear Coefficient of Thermal Expansion</b><br>Units of<br>10 <sup>-6</sup> / °F<br>(10 <sup>-6</sup> / °C) |                                                 |                    |                     |                     |
| <b>Temperature Range</b><br>-100 °F to +70 °F<br>(-73 °C to +21 °C)                                            |                                                 | 5.8<br>(10.4)      | 6.0<br>(10.8)       | 6.1<br>(11.0)       |
| +70 °F to 800 °F<br>(+21 °C to +427 °C)                                                                        | 6.3<br>(11.3)                                   | 6.5<br>(11.7)      | 6.8<br>(12.2)       | 7.2<br>(13.0)       |
| <b>Magnetic Permeability</b>                                                                                   | <b>Strongly Ferromagnetic in all Conditions</b> |                    |                     |                     |
| <b>Thermal Conductivity</b><br>Btu - ft / hr - ft <sup>2</sup> °F<br>(W / m - K)                               |                                                 |                    |                     |                     |
| 70 - 212 °F<br>(21 - 100 °C)                                                                                   | 10.6<br>(18.3)                                  | 10.3<br>(17.8)     |                     |                     |
| 70 - 932 °F<br>(21 - 500 °C)                                                                                   | 13.1<br>(22.7)                                  | 13.1<br>(22.7)     |                     |                     |
| <b>Electrical Resistivity</b><br>microhm-cm                                                                    | 98                                              | 77                 | 80                  | 86                  |

**MECHANICAL PROPERTIES**

|                              | Condition A | Condition H 900 | Condition H 1075 | Condition H 1150 |
|------------------------------|-------------|-----------------|------------------|------------------|
| <b>Modulus of Elasticity</b> |             |                 |                  |                  |
| 10 <sup>6</sup> psi (GPa)    | 28.5 (196)  | 28.5 (196)      | 28.5 (196)       | 28.5 (196)       |
| <b>Modulus of Rigidity</b>   |             |                 |                  |                  |
| 10 <sup>6</sup> psi (GPa)    | 11.2 (77.2) | 11.2 (77.2)     | 11.2 (77.2)      | 11.2 (77.2)      |

Room temperature tensile properties can vary substantially with heat treatment in the 900°F (482°C) to 1150°F (621°C) range. Values shown below are typical room temperature properties which could be expected for

|                                         | Condition A      | Condition H 900  | Condition H 1075 | Condition H 1150 |
|-----------------------------------------|------------------|------------------|------------------|------------------|
| <b>0.2% Offset Yield Strength</b>       |                  |                  |                  |                  |
| psi (MPa)                               | 110,000<br>760   | 180,000<br>1,240 | 135,000<br>930   | 125,000<br>860   |
| <b>Ultimate Tensile Strength</b>        |                  |                  |                  |                  |
| psi (MPa)                               | 150,000<br>1,030 | 195,000<br>1,340 | 155,000<br>1,070 | 145,000<br>1,000 |
| <b>Elongation</b><br>(percentage in 2") | 8                | 10               | 10               | 10               |
| <b>Hardness</b><br>Rockwell C scale     | 33               | 43               | 31               | 28               |

| <b>SUMMARY OF HEAT TREATING AL 17-4™ ALLOY</b>                                     |                                                                                       |                          |                            |             |
|------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|--------------------------|----------------------------|-------------|
| Minimum Properties Specified in Aerospace Material Specification (AMS) 5604        |                                                                                       |                          |                            |             |
| Heat Treat to Produce Martensitic Structure                                        | Precipitation Heat Treatment to Produce Desired Strength                              |                          |                            |             |
|                                                                                    | Precipitation Hardening Heat Treatment                                                | Yield Strength psi (MPa) | Tensile Strength psi (MPa) | Hardness Rc |
| <b>Solution Heat Treatment at 1950 °F (1066 °C)</b>                                | 900 °F (482 °C)<br>60 minutes<br>Condition H 900                                      | 170,000 (1170)           | 190,000 (1310)             | 40 to 47    |
|                                                                                    | 925 °F (496 °C)<br>4 Hours<br>Condition H 925                                         | 155,000 (1070)           | 170,000 (1170)             | 38 to 45    |
|                                                                                    | 1025 °F (552 °C)<br>4 Hours<br>Condition H 1025                                       | 145,000 (1000)           | 155,000 (1070)             | 35 to 42    |
|                                                                                    | 1075 °F (579 °C)<br>4 Hours<br>Condition H 1075                                       | 125,000 (860)            | 145,000 (1000)             | 33 to 39    |
|                                                                                    | 1100 °F (593 °C)<br>4 Hours<br>Condition H 1100                                       | 115,000 (790)            | 140,000 (965)              | 32 to 38    |
|                                                                                    | 1150 °F (621 °C)<br>4 Hours<br>Condition H 1150                                       | 105,000 (725)            | 135,000 (930)              | 28 to 37    |
|                                                                                    | 1400 °F (760 °C)<br>2 Hours +<br>1150 °F<br>4 Hours<br>Condition H 1150-M from SA 693 | 75,000 (515)             | 115,000 (790)              | 26 to 36    |
| <b>Condition A</b><br><i>(This is the condition furnished by Allegheny Ludlum)</i> |                                                                                       |                          |                            |             |

Data are typical and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those shown herein.

## HEAT TREATMENT

The AL 17-4 Precipitation Hardening Alloy is furnished in the annealed condition. This is also called the solution heat treated condition, or Condition A. Annealing is conducted by heat treating at approximately 1900°F (1040°C) to 1950°F (1065°C) and cooling to room temperature. In this condition, the material possesses a martensitic structure. As a martensitic structure, the AL 17-4 alloy possesses a relatively high strength and hardness in the annealed condition. The strength and hardness of the material is generally somewhat lower in the H 1150 overaged condition.

To develop further increase in strength, the annealed material is precipitation hardened by heat treatments at 900°F (482°C). Heat treatments above 1075°F (579°C) generally result in material softer than material in the annealed condition. The heat treatments are usually specified as follows:

The precipitation hardening reaction can be driven past peak strength by heat treating at an excessively high temperature or by excessive time at the precipitation hardening temperature. The table on page 3 shows the effect of higher temperature heat treatment. A less dramatic downward shift in strength results from excessively long precipitation hardening times.

The heat treatments used for the AL 17-4 Precipitation Hardening Alloy are summarized below.

| Condition | Temperature                  | Time              |
|-----------|------------------------------|-------------------|
| H 900     | 900 °F ± 10<br>(482 °C ± 5)  | 60 min. ± 5 min.  |
| H 925     | 925 °F ± 10<br>(496 °C ± 5)  | 4 hrs. ± 0.25 hr. |
| H 1025    | 1025 °F ± 10<br>(552 °C ± 5) | 4 hrs. ± 0.25 hr. |
| H 1075    | 1075 °F ± 10<br>(579 °C ± 5) | 4 hrs. ± 0.25 hr. |
| H 1100    | 1100 °F ± 10<br>(593 °C ± 5) | 4 hrs. ± 0.25 hr. |
| H 1150    | 1150 °F ± 10<br>(621 °C ± 5) | 4 hrs. ± 0.25 hr. |

*Data are typical and should not be construed as maximum or minimum values for specification or for final design. Data on any particular piece of material may vary from those shown herein.*

## WELDING AND BRAZING

The AL 17-4 Precipitation Hardening Alloy is readily welded using conventional inert gas methods used for stainless grades. Preheating is not usually required. Postweld heat treating is needed to produce the various precipitation hardened heat treatment properties.

If matching filler material is used, properties comparable to those of the parent metal can be produced in the weld by postweld precipitation hardening heat treatment.

When a number of welding passes are made, a substantial thermal cycling has been conducted on the material. More uniform mechanical properties can be obtained by solution annealing the material before conducting precipitation hardening heat treatments. The solution anneal has the effect of minimizing the effects of the thermal cycling.

In the case of welding with non-matching filler, an austenitic stainless steel such as 308L or other ductile austenitic should be used. This filler will not produce the precipitation hardening response, however.

## FORMING

The tensile data for the AL 17-4 Precipitation Hardening Alloy indicate that the alloy does not possess the high tensile elongation characteristic of the austenitic stainless steels. The material is capable of being mildly formed but is not capable of being severely formed. Forming is more easily accomplished in the overaged (such as H 1150-M from SA 693) condition than in the annealed, condition.