

# STEREOLITHOGRAPHY ABS-LIKE WHITE

Current Supplier Material:  
[Accura Xtreme White 200](#)



## PRODUCT DESCRIPTION

ABS-Like White is a widely used, all-purpose material that provides flexibility relative to other SLA resins. It is an ideal stereolithography material for durability. Compared to the average value for injection-molded ABS, it will have a slightly higher tensile strength but lower elongation at break. ABS-Like White's heat deflection is the lowest of all SLA materials.

## APPLICATIONS

ABS-Like White's well-rounded mechanical properties make it suitable for form-and-fit prototypes, snap-fit assemblies, consumer electronic components, and medical device prototypes.



## KEY PRODUCT BENEFITS

- Good strength and flexibility
- Durability
- Dimensional Stability

## PROPERTIES

PROPERTY	TEST METHOD	VALUE
Color	-	White
Density in solid state*	@ 25 °C (77 °F)	1.18 g/cm <sup>3</sup>
Water absorption (20 °C, 50% relative humidity)	ASTM D570	0.65 ± 0.15%
E-module (x-y plane)	ASTM D638, test speed 10mm/min.	3,300 ± 400 MPa
Tensile strength (x-y plane)		55 ± 10 MPa
Elongation at break (x-y plane)		9 ± 5%
Heat deflection temperature @ 0.46 MPa*	ASTM D648	47 °C (117 °F)
Heat deflection temperature @ 1.82 MPa*		42 °C (108 °F)

[\\*From supplier data sheet](#)

## TOLERANCES

For well-designed parts, tolerances in the X/Y dimension of ±0.002 in. (0.05mm) for the first inch plus ±0.001 in./in., and Z-dimension tolerances of ±0.005 in. (0.127mm) for the first inch plus ±0.001 in./in. (0.001mm/mm), can typically be achieved. Note that tolerances may change depending on part geometry.

Version 1.0 | December 2019