




ULTEM® 2200**GE Plastics - Polyether Imide**Unit System: English **View****Datasheet** **Shown Below**ASTM Data Sheet 

ISO Data Sheet --

CAMPUS® Data Sheet --

ActionsProduct Sourcing E-mail a Datasheet Product Alternatives **General Information****Product Description**

20% Glass fiber filled, standard flow Polyetherimide (Tg 217C). ECO Conforming, UL94 V0 and 5VA listing. NSF 51 listing, WRAS certification in recognized colors.

General

Material Status	● Commercial: Active
Availability	● North America
Test Standards Available	● ASTM
Filler/Reinforcement	● Glass fiber reinforcement, 20 % Filler by Weight
Agency Ratings	● NSF 51
Forms	● Pellets
Processing Method	● Injection Molding
Multi-Point Data	<ul style="list-style-type: none"> ● Coefficient of Thermal Expansion vs. Temperature (ASTM E831) ● Elastic Modulus vs Temperature (ASTM D4065) ● Flexural DMA (ASTM D4065) ● Instrumented Impact (Energy) (ASTM D3763) ● Instrumented Impact (Load) (ASTM D3763) ● Pressure-Volume-Temperature (PVT - Zoller Method) ● Shear DMA (ASTM D4065) ● Specific Heat vs. Temperature (ASTM D3417) ● Tensile Creep (ASTM D2990) ● Tensile Fatigue ● Tensile Stress vs. Strain (ASTM D638) ● Thermal Conductivity vs. Temperature (ASTM E1530) ● Viscosity vs. Shear Rate (ASTM D3835)

ASTM and ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density -Specific Gravity	1.42	sp gr 23/23°C	ASTM D792
Melt Mass-Flow Rate (MFR) (337°C/6.6 kg)	6.00	g/10 min	ASTM D1238
Mold Shrink, Linear-Flow (0.126 in)	0.0030 to 0.0050	in/in	ASTM D955
Water Absorption @ 24 hrs	0.19	%	ASTM D570
Water Absorption @ Equil (73 °F)	1.1	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ²	1.00E+6	psi	ASTM D638
Tensile Strength @ Break ³	19000	psi	ASTM D638
Tensile Elongation @ Brk ³	4.0	%	ASTM D638
Flexural Modulus (3.94 in Span) ⁴	1.00E+6	psi	ASTM D790
Flexural Strength @ Break (3.94 in Span) ⁴	33000	psi	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73 °F)	1.20	ft-lb/in	ASTM D256
Unnotched Izod Impact (73 °F)	9.00	ft-lb/in	ASTM D256
Reverse Notch Izod Impact (0.126 in)	8.7	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	114		ASTM D785
Thermal	Nominal Value	Unit	Test Method
DTUL @66psi - Unannealed (0.252 in)	410	°F	ASTM D648
DTUL @264psi - Unannealed (0.252 in)	410	°F	ASTM D648
Vicat Softening Point (Rate B, Loading 2 (50 N))	428	°F	ASTM D1525
CLTE, Flow (TMA) (-4 to 302°F (-20 to 150°C))	0.000014	in/in/°F	ASTM E831
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	7.0E+16	ohm-cm	ASTM D257
Dielectric Strength (0.0630 in, in Oil)	670	V/mil	ASTM D149
Dielectric Constant (1000 Hz)	3.500		ASTM D150
Dissipation Factor			ASTM D150
(1000 Hz)	0.0015		
(2E+9 Hz)	0.0049		
Arc Resistance (PLC) (Tungsten Electrode)	PLC 6		ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating - UL			UL 94
(0.0160 in)	V-0		
(0.0750 in)	5VA		
Limiting Oxygen Index	50	%	ASTM D2863
UL 746	Nominal Value	Unit	Test Method
Rel Temp Indx Mech w/olmp	338	°F	UL 746
Rel Temp Indx Mech w/lmp	338	°F	UL 746
Rel Temp Indx Elect	338	°F	UL 746
Comparative Tracking Index (CTI) (PLC)	PLC 4		UL 746
High Voltage Arc Tracking Rate (HVTR) (PLC)	PLC 2		UL 746
Hot-wire Ignition (HWI) (PLC)	PLC 1		UL 746
High Amp Arc Ignition (HAI) (PLC)	PLC 4		UL 746

Additional Properties

The value listed as Unnotched Izod Impact, ASTM D256, was tested in accordance with ASTM D4812.
 CSA File No. (See File for Complete Listing): LS88480
 NBS Smoke Density, ASTM E662, Flaming, Ds 4 min: 1.3

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	300	°F
Drying Time	4.0 to 6.0	hr
Drying Time, Maximum	24	hr
Suggested Max Moisture	0.020	%
Suggested Shot Size	40 to 60	%
Rear Temperature	630 to 750	°F
Middle Temperature	640 to 750	°F
Front Temperature	650 to 750	°F
Nozzle Temperature	650 to 750	°F
Processing (Melt) Temp	660 to 750	°F
Mold Temperature	275 to 325	°F
Back Pressure	50.0 to 100.0	psi
Screw Speed	40 to 70	rpm
Vent Depth	0.0010 to 0.0030	in

Notes

Typical properties: these are not to be construed as specifications.

Ø.2 in/min

Type I, 0.2 in/min

0.1 in/min



Copyright ©, 105 [IDES - One Source. Plastics Data.](#)

The information presented on this data sheet was acquired by IDES from various sources, including the producer of the material and recognized testing agencies. In some cases, material updates have been integrated directly into the IDES Plastics Database by the material producer utilizing the [Data Maintenance Tool](#). IDES makes substantial efforts to assure the accuracy of this data. However, IDES assumes no responsibility for the data values and urges that upon final material selection, data points are validated with the manufacturer.